

Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) EP 0 979 968 A2

(12)

EUROPEAN PATENT APPLICATION

(43) Date of publication:
16.02.2000 Bulletin 2000/07

(51) Int Cl.7: **F16L 11/04**, B29C 59/14,
C08J 7/06, B32B 1/08
// B29K27:12

(21) Application number: 99306286.8

(22) Date of filing: 09.08.1999

(84) Designated Contracting States:
AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE
Designated Extension States:
AL LT LV MK RO SI

(30) Priority: 10.08.1998 JP 22508798
10.08.1998 JP 22508898

(71) Applicant: **TOKAI RUBBER INDUSTRIES, LTD.**
Komaki-shi, Aichi-ken, 485-8550 (JP)

(72) Inventors:
• **Katayama, Kazutaka**
Komaki-shi, Aichi 485-0029 (JP)

• **Ito, Hiroaki**
Kasugai-shi, Aichi 487-0035 (JP)
• **Nishiyama, Takahiro**
Kasugai-shi, Aichi 486-0903 (JP)
• **Murakami, Koyo**
Nagoya-shi, Aichi 464-0035 (JP)
• **Hayakawa, Tomonori**
Tokai-shi, Aichi 476-0002 (JP)

(74) Representative: **Frankland, Nigel Howard**
FORRESTER & BOEHMERT
Franz-Joseph-Strasse 38
80801 München (DE)

(54) Method of producing fuel hose and fuel hose obtained thereby

(57) A method of producing a fuel hose having superior adhesive reliability with superior initial adhesive strength between a tubular fluororesin inner layer (1) and a thermoplastic resin outer layer (2) and with restrained deterioration in adhesive strength after heat aging and immersion into fuel under severe conditions such as an inside of an engine compartment. The method includes plasma treatment on a peripheral surface of the tubular fluororesin inner layer, at least one treatment of water treatment and silane coupling agent treatment on the plasma-treated surface and formation of the thermoplastic resin outer layer on the treated peripheral surface. Thus, the functional groups having fluorine atoms not involved in adhesion go inside the tubular fluororesin inner layer by conducting the at least one treatment of water treatment and silane coupling agent aqueous solution treatment so that the surface concentration of fluorine atoms sufficiently decreases on the peripheral surface of the tubular fluororesin inner layer and adhesive functional groups (functional groups having oxygen atoms) such as an OH group are widely distributed therein. As a result, adhesive strength between the tubular fluororesin inner layer and the thermoplastic resin outer layer is improved so that deterioration in adhesive strength after heat aging and immersion into fuel can be restrained under severe conditions such as an inside of an engine compartment, for obtaining a fuel hose superior in adhesive reliability.




Fig. 1

Description**FIELD OF THE INVENTION**

5 [0001] The present invention relates to a method of producing a fuel hose for use in a fuel system of a motor vehicle or other equipment and a fuel hose obtained thereby.

PRIOR ART

10 [0002] Generally, fuel hoses used in fuel systems of cars and other equipment have multi-layer structures comprising various rubber-and resin layers. Among such multi-layer fuel hoses, a two-layer fuel hose comprising a fluororesin inner layer and a thermoplastic resin outer layer laminated on a peripheral surface of the inner layer is in prevalent use. Since a fluororesin is superior not only in corrosion resistance and impermeability to chemicals, gasoline and the like but also in resistance to sour gasoline which is produced by oxidation of gasoline (sour gasoline resistance), a
15 fluororesin is generally regarded as the optimal material for forming an inner layer of a fuel hose which is directly exposed to fuel. The thermoplastic resin outer resin layer is provided as a reinforcing member of the hose for imparting pressure resistance and other dynamic characteristics to the fuel hose.

[0003] However, since the fluororesin for forming the inner layer of the hose has very little adhesiveness for other structural materials, there is a problem caused that adhesive strength between the fluororesin inner layer and the thermoplastic resin outer layer is extremely low even if the two layers are adhered by an adhesive. Proposed as one
20 approach for solving the aforesaid problem is a fuel hose comprising a fluororesin inner layer with its surface modified with treatment such as corona discharge (high-frequency treatment) and a thermoplastic resin outer layer formed on the surface-treated fluororesin inner layer. Such a hose is commercially available for use as a fuel hose for cars and the like, for example, as a fuel hose of a gasoline tank.

25 [0004] However, such a fuel hose surface-modified by corona discharge or the like does not have a sufficient initial adhesive strength between the fluororesin inner layer and the thermoplastic resin outer layer. For this reason, when the above-mentioned fuel hose is used under severe conditions such as an inside of an engine compartment, the hose is directly subject to effects due to a temperature rise in the atmosphere, engine vibration and the like so that the adhesive strength between the fluororesin inner layer and the thermoplastic resin outer layer remarkably deteriorates
30 after heat aging and immersion into fuel, resulting in a problem of inferiority in adhesive reliability.

[0005] In view of the foregoing, it is an object of the present invention to provide a method of producing a fuel hose which is superior in an initial adhesive strength between a fluororesin inner layer and a thermoplastic resin outer layer and can restrain-deterioration in adhesive strength after heat aging and immersion into fuel under severe conditions such as an inside of an engine compartment, resulting in adhesive reliability, and a fuel hose produced thereby.

35 [0006] In accordance with a first aspect of the present invention, there is provided a method of producing a fuel hose comprising plasma-treating a surface of a tubular fluororesin inner layer, treating a surface layer of the plasma-treated peripheral surface with at least one of water and a silane coupling agent aqueous solution and forming a thermoplastic resin outer layer on the treated peripheral surface. In accordance with a second aspect of the present invention, there is provided a fuel hose produced by the above-mentioned method.


SUMMARY OF THE INVENTION

40 [0007] The inventors of the present invention already have found that adhesive strength between the tubular fluororesin inner layer and the thermoplastic resin outer layer was improved by plasma-treating a surface of the tubular fluororesin inner layer so that superior initial adhesive strength can be obtained. This is because fluorine atoms and hydrogen atoms are set free from molecules of the fluororesin by the plasma treatment so as to produce carbon radicals, which react with the atmosphere so as to produce adhesive functional groups, the surface concentration of fluorine atoms decreases by defluorination, and the plasma-treated peripheral surface becomes uneven. As a result of further
45 researches on the plasma-treated fuel hose, the inventors found that the surface concentration of fluorine atoms is still high on the peripheral surface of the tubular fluororesin inner layer and functional groups having fluorine atoms not involved in adhesion are widely distributed therein by conducting plasma treatment only so that adhesive strength between the tubular fluororesin inner layer and the thermoplastic resin outer layer is insufficient. As a result of still
50 further researches, the inventors found that the functional groups having fluorine atoms not involved in adhesion go inside the tubular fluororesin inner layer by conducting at least one of water treatment and silane coupling agent aqueous solution treatment on the plasma-treated peripheral surface so that the surface concentration of fluorine atoms decreases on the peripheral surface of the tubular fluororesin inner layer and the distribution of the functional groups having fluorine atoms not involved in adhesion decreases while adhesive functional groups (functional groups having oxygen atoms.) such as an OH group widely distribute therein. As a result, the inventors found that adhesive strength
55

between the tubular fluororesin inner layer and the thermoplastic resin outer layer is improved by conducting the at least one of water treatment and silane coupling agent aqueous solution treatment on the plasma-treated peripheral surface. As a result, a fuel hose superior in adhesive reliability can be obtained since deterioration in adhesive strength after heat aging and immersion into fuel can be restrained under severe conditions such as an inside of an engine compartment. Thus, the inventors have attained the present invention. Especially, in the case that silane coupling agent aqueous solution treatment is conducted on the plasma-treated peripheral surface, a silane coupling agent layer can be formed on a surface of the tubular fluororesin inner layer so that each adhesive strength between the tubular fluororesin inner layer and the silane coupling agent layer and between the silane coupling agent layer and the thermoplastic resin outer layer is further improved, respectively.

[0008] where the water treatment is conducted by using an aqueous acid solution, sufficient adhesive strength after heat aging and immersion into fuel can be obtained so that a fuel hose further superior in adhesive reliability can be produced. Where a hydrogen exponent (pH) of the aqueous acid solution is 2 to 6, a fuel hose even further superior in adhesive reliability can be produced.

[0009] Where the silane coupling agent is an amino silane coupling agent represented by the following general formula (1), stability of the silane coupling agent aqueous solution is good.




wherein Y is $NH_2(CH_2)_n-$, $NH_2(CH_2)_nNH(CH_2)_m-$ or $NH_2CONH(CH_2)_n-$, wherein n and m are 0 to 5, respectively, X^1 , X^2 and X^3 , which are the same or different, are $-CH_3$, $-OCR_3$, $-OC_2H_5$ or $-OC_2H_4OCH_3$, respectively, wherein at least two of X^1 , X^2 and X^3 are $-OCH_3$, $-OC_2H_5$ or $-OC_2H_4OCH_3$.


[0010] Where the concentration of the silane coupling agent is not more than 10% by weight of a total amount of the aqueous solution, it becomes easy to treat the plasma-treated peripheral surface therewith.

[0011] Where a hydrogen exponent (pH) of the acid silane coupling agent aqueous solution is 2 to 6, sufficient adhesive strength after heat aging and immersion into fuel can be obtained, resulting in superior adhesive reliability.


[0012] Where the silane coupling agent is an epoxy silane coupling agent represented by the following general formula (2), stability of the silane coupling agent aqueous acid solution is improved.



wherein Z is



or



wherein n is 0 to 5,

X^1 , X^2 and X^3 , which are the same or different, are $-\text{CH}_3$, $-\text{OCH}_3$, $-\text{OC}_2\text{H}_5$ or $-\text{OC}_2\text{H}_4\text{OCH}_3$, respectively, wherein at least two of X^1 , X^2 and X^3 are $-\text{OCH}_3$, $-\text{OC}_2\text{H}_5$ or $-\text{OC}_2\text{H}_4\text{OCH}_3$.

[0013] Where the concentration of the silane coupling agent is not more than 10% by weight of a total amount of the aqueous acid solution, it becomes easy to treat the plasma-treated peripheral surface with the silane coupling agent.

BRIEF DESCRIPTION OF THE DRAWINGS

[0014]

Fig. 1 is a view illustrating the structure of one embodiment of a fuel hose according to the present invention;
 Fig. 2 is a view illustrating the structure of another embodiment of a fuel hose according to the present invention;
 Fig. 3 is a view illustrating the structure of still another embodiment of a fuel hose according to the present invention;
 Fig. 4 is an explanatory view of one embodiment of a method of producing a fuel hose according to the present invention;
 Fig. 5 is an explanatory view of another embodiment of the treatment vessel 12 of Fig. 4;
 Fig. 6 is an explanatory view of another embodiment of the treatment vessel 13 of Fig. 4;
 Fig. 7 is an explanatory view of one embodiment of a method using a vacuum plasma treatment apparatus having auxiliary vacuum chambers according to the present invention;
 Fig. 8 is a view illustrating the structure of one embodiment of a sealed portion of the vacuum plasma treatment apparatus;
 Fig. 9 is a view illustrating the structure of another embodiment of a sealed portion of the vacuum plasma treatment apparatus;
 Fig. 10 is an explanatory view illustrating one embodiment of a method of producing a fuel hose according to the present invention by using a vacuum plasma treatment apparatus having an induction coil electrode means;
 Fig. 11 is an explanatory view illustrating one embodiment of a method of producing a fuel hose according to the present invention wherein a cooling zone is installed.
 Fig. 12 is an explanatory view illustrating one embodiment of a method of producing a fuel hose according to the present invention by using a mandrel;
 Fig. 13 is a view illustrating the structure of a corona discharge apparatus used for a method of producing a fuel hose of COMPARATIVE EXAMPLE;
 Fig. 14 is a view illustrating the structure of a test piece used for determination of adhesive strength of a fuel hose;
 Fig. 15 is a chart of data by ESCA analysis on a peripheral surface of a tubular fluororesin inner layer; and
 Fig. 16 is a chart of data by ESCA analysis on a peripheral surface of a tubular fluororesin inner layer.

DETAILED DESCRIPTION OF THE INVENTION

[0015] The present invention will hereinafter be described in detail by way of embodiments thereof.

[0016] The fuel hose of the present invention comprises a tubular fluororesin inner layer 1 and a thermoplastic resin outer layer 2 formed on a peripheral surface of the tubular fluororesin inner layer 1, as shown in Fig. 1. The main feature of the present invention is that a peripheral surface 1a of the tubular fluororesin inner layer 1 is plasma-treated and further at least one of water treatment and silane coupling agent aqueous solution treatment is conducted thereon.

[0017] The fluororesin for forming the tubular fluororesin inner layer 1 is not particularly limited. Exemplary materials include an ethylene-tetrafluoroethylene copolymer (ETFE), polyvinylidene fluoride (PVDF), polychlorotrifluoroethylene (CTFE), an ethylene-chlorotrifluoroethylene copolymer (ECTFE), a hexafluoropropylene-tetrafluoroethylene copolymer (FEP), polytetrafluoroethylene (PTFE); a tetrafluoroethylene-perfluoroalkoxyethylene terpolymer, a vinylidene fluoride-tetrafluoroethylene copolymer, a vinylidene fluoride-hexafluoropropylene copolymer, a tetrafluoroethylene-hexafluoropropylene-vinylidene fluoride terpolymer (THV). These may be used either alone or in combination thereof. Among all, ETFE, PVDF and THV are preferred from a viewpoint of high impermeability to gasoline and moldability.

[0018] It is preferred to add a conductive agent to the fluororesin to dissipate static electricity generated as a fuel (such as gasoline) flows down the hose. Examples thereof include carbon black and finely divided stainless steel filaments. The proportion of the conductive agent is preferably within a range of 0.5 to 30 parts by weight (hereinafter, abbreviated to parts) relative to 100 parts of fluororesin. Where the proportion is within the above range, volume resistivity of the tubular fluororesin inner layer 1 is not more than $10^{10} \Omega \cdot \text{cm}$ so that the static electricity can be discharged from the hose. As a result, accidents such as ignition of the fuel by the accumulated static electricity can be reduced.

[0019] For improved physical properties, fillers can appropriately be added to the fluororesin. Examples thereof include titanium dioxide, barium sulfate, calcium carbonate, silica, carbon black, magnesium silicate, aluminum silicate, zinc oxide, alumina, calcium sulfate, aluminum sulfate, calcium hydroxide, aluminum hydroxide, talc, molybdenum

dioxide, whiskers, short staple fibers, 'graphite and metallic powder. These may be used either alone or in combination thereof. The proportion of the tiller is preferably not more than 30 parts relative to 100 parts of the fluororesin.


[0020] The method of plasma-treating the surface of the tubular fluororesin inner layer 1 is not particularly limited. Examples thereof include vacuum plasma treatment wherein the surface is exposed to a plasma atmosphere generated by gas-introduction for electrical discharge into a chamber maintained at a vacuum or reduced pressure and application of high-frequency. Another example is atmospheric plasma treatment wherein the surface is exposed to a plasma atmosphere generated by gas-introduction for electrical discharge into a chamber maintained at an atmospheric pressure and application of high-frequency. Among all, the vacuum plasma treatment is preferred because uniform treatment can be easily obtained. As the electric discharge gas, it is preferred to use a gas containing Ar. Examples of the gas containing Ar include Ar gas alone and a mixed gas of Ar and N₂, H₂, O₂ or the like. Where the mixed gas is used, it is preferred that the proportion of the Ar gas is not less than 50% by volume of the total mixed gas.

[0021] It is preferred that water excluding metal ions is used for the water treatment on the plasma-treated peripheral surface. Examples thereof include pure water (pH=7). Especially, it is preferred to use an aqueous acid solution wherein acetic acid, formic acid, hydrochloric acid, phenol or the like is diluted with water. It is preferred that a hydrogen exponent (pH) of the aqueous acid solution is 2 to 6.

[0022] The method of the water treatment is not particularly limited. Examples thereof include a water-dripping method, a water-atomizing method, a method by applying water with a brush or a spray, a dipping-in-water method, a method by scattering water using an ultrasonic oscillator, and a method by introduction into a high-temperature and high-humidity vessel with saturated vapor.

[0023] Examples of the silane coupling agent aqueous solution for the method of the treatment using the same on the plasma-treated peripheral surface include a dilution of silane coupling agent with water (such as pure water) and a dilution of silane coupling agent with an aqueous acid solution (such as an acetic aqueous acid solution). It is preferred that the hydrogen exponent (pH) of the silane coupling agent aqueous solution is 2 to 6.


[0024] The silane coupling agent is not particularly limited, but is preferably an amino silane coupling agent represented by the following general formula (1) due to its stability in an aqueous solution in the case that it is dissolved in water.




wherein Y is NH₂(CH₂)_n-, NH₂(CH₂)_nNH(CH₂)_m- or NH₂CONH(CH₂)_n-, wherein n and m are 0 to 5, respectively, X¹, X² and X³, which are the same or different, are -CH₃, -OCH₃, -OC₂H₅ or -OC₂H₄OCH₃, respectively, wherein at least two of X¹, X² and X³ are -OCH₃, -OC₂H₅ or -OC₂H₄OCH₃.

[0025] Among the amino silane coupling agents represented by the general formula (1), N-β (aminoethyl)γ-amino propylmethyldimethoxysilane, N-β(aminoethyl)γ-aminopropyltriethoxysilane, γ-aminopropyltrimethoxysilane, γ-aminopropyltriethoxysilane are especially preferred.


[0026] An epoxy silane coupling agent represented by the following general formula (2) is preferred due to its stability in an aqueous acid solution in the case that it is dissolved in the aqueous acid solution.



wherein Z is



or



wherein n is 0 to 5,

X¹, X² and X³, which are the same or different, are -CH₃, -OCH₃, -OC₂H₅ or -OC₂H₄OCH₃, respectively, wherein at least two of X¹, X² and X³ are -OCH₃, -OC₂H₅ or -OC₂H₄OCH₃.

[0027] Among the epoxy silane coupling agents represented by the general formula (2), β-(3,4-epoxycyclohexyl) ethyltrimethoxysilane and γ-glycidoxypropyltrimethoxysilane are especially preferred.

[0028] The concentration of the silane coupling agent is preferably not more than 10%, by weight of the total aqueous solution, more preferably not more than 5% by weight. If the concentration exceeds 10% by weight, gelation may occur in the aqueous solution so that uniform application may not be realized. In addition, the concentration of the silane coupling agent in the aqueous acid solution is preferably within the above-mentioned range.

[0029] The method of the treatment using the silane coupling agent aqueous solution or the silane coupling agent aqueous acid solution is not particularly limited as long as the aqueous solution can be applied uniformly on the plasma-treated peripheral surface. Examples thereof include a method of dripping the aqueous solution, a method of atomizing it, a method by applying it with a brush or a spray, a method of dipping therein, and a method by scattering it using an ultrasonic oscillator.

[0030] The amount of the silane coupling agent (excluding solvent) to be applied is preferably within a range of 1 × 10⁻⁸ to 1 × 10⁻⁴ g/cm², more preferably within a range of 1 × 10⁻⁸ to 1 × 10⁻⁵ g/cm² to the surface layer of 1 cm² of the plasma-treated peripheral surface of the tubular fluororesin in inner layer 1. The amount less than 1 × 10⁻⁹ g/cm² is too small so that adhesive strength between the tubular fluororesin inner layer 1 and the thermoplastic resin outer layer 2 is inferior, while the amount greater than 1 × 10⁻⁴ g/cm² is too much so that foaming occurs on the thermoplastic resin outer layer 2.

[0031] To impart structural strength to the fuel hose, the thermoplastic resin outer layer 2 is formed onto the peripheral surface 1a of the tubular fluororesin inner layer 1 treated with plasma and at least one of water and silane coupling agent aqueous solution. The thermoplastic resin for forming the thermoplastic resin outer layer 2 is not particularly limited. Examples thereof include polyester resins such as a polyamide resin and polybutylene terephthalate (PBT), a urethane resin, a polyolefin resin and modified resins thereof. These may be used either alone or in combination. Among all, a polyamide resin is preferred due to their superiority in heat resistance and hydrolyzability. Examples of the polyamide resin include nylon 6, nylon 66, nylon 11 and nylon 12, among which nylon 11 and nylon 12 are especially preferred due to their superiority in moldability and resistance to antifreezing agents.

[0032] It is preferred to add a conductive agent to the thermoplastic resin to impart conductivity to the thermoplastic resin outer layer 2. The kind and the proportion of the conductive agent are the same as those of the tubular fluororesin inner layer 1 as described above.

[0033] For improved processability and flexibility, a plasticizer may be added to the thermoplastic resin, as required. Examples thereof include sulfonamides and hydroxybenzoic esters. The proportion of the plasticizer is preferably not more than 20 parts relative to 100 parts of the thermoplastic resin.

[0034] As shown in Fig. 2, another embodiment of the present invention comprises a tubular fluororesin inner layer 1, a thermoplastic resin intermediate layer 2 formed on a peripheral surface 1a of the tubular fluororesin inner layer 1 and an outer layer 18 of rubber (or thermoplastic elastomer) formed on a peripheral surface of the thermoplastic resin intermediate layer 2. The fuel hose having such an outer layer 18 is preferred for its high flame resistance and high resistance to chipping.

[0035] The material for forming a rubber outer layer 18 is not particularly limited. Examples thereof include epichlorohydrin rubber (CO), epichlorohydrin-ethylene oxide equimolar copolymer (ECO, alias CHC), acrylonitrile-butadiene copolymer rubber (NBR), NBR-polyvinyl chloride (PVC) blend rubber (NBR/PVC), chloroprene rubber (CR), chlorosulfonated polyethylene (CSM), chlorinated polyethylene (CPE), ethylene-propylene-diene rubber (EPDM), ethylene-propylene rubber (EPM), NBR/EPDM blend rubber and fluorocarbon rubber (FKM). These may be used either alone or in combination. Among all, CO, ECO, NBR/PVC, CSM, EPDM and EPM are preferred for their high heat resistance, and high ozone resistance. Further, the materials for forming a thermoplastic elastomer outer layer 18 are not partic-

ularly limited. Examples thereof include thermoplastic elastomers such as olefinic elastomers, polyvinyl chloride elastomers and urethane elastomers. The thickness of the outer layer 18 is generally within a range of 0.5 to 5.0mm, preferably 0.5 to 3.0mm.

[0036] As shown in Fig. 3, still another embodiment of the present invention comprises a tubular fluororesin inner layer 1, a thermoplastic resin intermediate layer 2 formed on a peripheral surface 1a of the tubular fluororesin inner layer 1, a reinforcing cord layer 19 formed on a peripheral surface of the thermoplastic resin intermediate layer 2 and an outer layer 19 of rubber (or thermoplastic elastomer) formed on a peripheral surface of the reinforcing cord layer 19. This fuel hose has the same structure as that of Fig. 2, except that the reinforcing cord layer 19 is installed between the thermoplastic resin intermediate layer 2 and the outer layer 18. Such a fuel hose containing the reinforcing cord layer 19 is preferred for its superior pressure resistance. The reinforcing cord layer 19 is formed by braiding natural fiber such as linen or cotton, a synthetic yarn such as polyester yarn, vinylon yarn or nylon yarn, or metal filaments such as wires.

[0037] In addition, each of the tubular fluororesin inner layer 1 and the thermoplastic resin outer layer 2 of the fuel hose of the present invention is not particularly limited to a single-layer structure, as shown in Figs. 1 to 3, respectively, and may have a multi-layer structure. For example, the tubular fluororesin inner layer 1 may have a two-layer structure wherein an inner layer is formed of conductive fluororesin and an outer layer is formed of non-conductive fluororesin. Alternatively, the tubular fluororesin inner layer 1 may have a two-layer structure wherein an inner layer is formed into a thin layer using a conductive fluororesin and an outer layer is formed of a non-conductive fluororesin.

[0038] The fuel hose of the present invention may, for example, be produced by the following manner. First, the material (such as fluororesin) for forming the tubular fluororesin inner layer 1 is extruded by an inner layer extruder 3, for obtaining the tubular fluororesin inner layer 1, as shown in Fig. 4. The tubular fluororesin inner layer 1 is introduced in a reaction chamber 6 of a vacuum plasma apparatus 5 and is plasma-treated in a plasma treatment zone between electrodes 9a. The plasma-treated tubular fluororesin inner layer 1 is introduced in a treatment vessel 12 where water is dripped thereon by a nozzle 12a. Next, the thus treated tubular fluororesin inner layer 1 is introduced in a treatment vessel 13 where excessive water is dried and eliminated by an air blowing apparatus 13a. Successively, the material (such as thermoplastic resin) for forming the thermoplastic resin outer layer 2 is extruded from an outer layer extruder 14 and the thermoplastic resin outer layer 2 is formed on a peripheral surface of the tubular fluororesin inner layer 1. Then, the thus obtained tube is wound up by a winder 15, for obtaining the intended fuel hose (as shown in Fig. 1). In addition, the fuel hose as the above (as shown in Fig. 1) can be obtained by dripping a silane coupling agent aqueous solution instead of water.

[0039] For establishing a stable plasma, the atmosphere in the reaction chamber 6 is evacuated by a vacuum pump 7, and then supplied with an electric discharge gas (containing Ar) by a gas supply apparatus 8. The reaction chamber 6 is maintained at a vacuum or reduced pressure (generally, 0.005 to 8 Torr). In the plasma treatment, an impedance-matched high-frequency, high-output current is applied to the electrodes 9a for a predetermined period by means of a high-frequency power source 10 and a matching box 11 to induce an electric discharge between the electrodes and thereby ionize the electric discharge gas to create a plasma state. The frequency used is in the range of 0.1 to 1000MHz, preferably 1 to 100 MHz. The output of the high-frequency power source 10 is generally within a range of 2 to 400W, preferably 5 to 300W. The treatment time is appropriately determined depending on the type and size of the fluororesin material but is generally 1 to 180 seconds, preferably 3 to 60 seconds. The vacuum plasma treatment is preferably a glow discharge plasma treatment using an Ar gas-containing atmosphere. Since this glow discharge plasma treatment does not require a high degree of vacuum, it is advantageous that the vacuum plasma apparatus to be used herein is not necessarily high performance but rather may be an ordinary apparatus.

[0040] The plasma treatment is carried out preferably at a subatmospheric or negative pressure. If sealing effect of seals 4 of the vacuum plasma apparatus 5 is poor, it is difficult to control the degree of vacuum within the vacuum plasma apparatus 5 at a constant level so that a stable plasma cannot be generated. For this reason, the seals 4 are preferably formed of rubber elastomer. The rubber elastomer with a hardness of 45 to 80 (JIS A) is generally preferred. The kind of the rubber elastomer is not particularly limited, but good results are obtained by using silicone rubber or acrylonitrile-butadiene copolymer rubber (NBR).

[0041] In the embodiment of Fig. 4, the water-dripping method is used, as described above, wherein water is dripped by the nozzle 12a in the treatment vessel 12. However, as shown in Fig. 5, the water treatment may be conducted by heating water using a heater 12d so as to be saturated in a vessel 12c and introducing the tubular fluororesin inner layer 1 in the vapor-saturated, high-temperature and high-humid vessel 12c. In this case, there is the advantage that water containing metal ions (such as tap water) can be used. This is because metal salts are not gasified, and sink and accumulate on the bottom of the treatment vessel 12 so as not to affect the water treatment to the tubular fluororesin inner layer 1.

[0042] In the embodiment of Fig. 4, water is dried so as to be eliminated by the method using the air blower 13a in the treatment vessel 13. However, as shown in Fig. 6, excessive water can be eliminated by passing the tubular fluororesin inner layer 1 through a packing 13b installed in a production line.

[0043] The configuration of the seal 4 is not particularly limited to a one-step structure, as shown in Fig. 4 and may have a two-step structure with auxiliary vacuum chambers 23. In Fig. 7, the same components as shown in Fig. 4 are denoted by the same reference numerals. Each auxiliary vacuum chamber 23 is separated from the reaction chamber 6 by a divider 24 and this auxiliary vacuum chamber 23 is communicated with a vacuum pump 26 via a line 22. In the Fig. 7, the reference numerals 25 indicate valves installed in the line 22. The internal pressure within the auxiliary vacuum chamber 23 is moderately reduced (about 0.1 to 10 Torr) by the vacuum pump 26, as compared with the reaction chamber 6. With this provision of the auxiliary vacuum chambers 23, the entry of external air from the hose inlet and outlet into the vacuum plasma apparatus 5 can be completely prevented. As a result, the degree of vacuum within the reaction chamber 6 can be exactly controlled so as to ensure generation of a stable plasma. The configuration of the seal 4 is not particularly limited to the above-mentioned figures formed of rubber elastomer. The seal 4 may be a generally frustoconical seal 4a, as shown in Fig. 8. With this seal 4a, the area of contact with the tubular fluororesin inner layer 1 is reduced to lower the contact frictional force. Consequently, the tubular fluororesin inner layer 1 can be smoothly introduced into the vacuum plasma apparatus 5 and also the vacuum plasma apparatus 5 can be kept sufficiently air-tight. In Fig. 8, an arrow indicates the entry direction of advance of the tubular fluororesin inner layer 1. As an alternative, the seal may be a disk-shaped seal 4b as shown in Fig. 9, whereby the air-tightness of the vacuum plasma apparatus 5 is further enhanced.

[0044] The plasma apparatus of the present invention is not particularly limited to the vacuum plasma apparatus 5, as shown in Fig. 4, having internal electrodes 9a, but may be an apparatus 5 provided with induction coil electrodes 9b on a periphery thereof as shown in Fig. 10. In Fig. 10, the same components as shown in Fig. 4 are denoted by the same reference numerals.

[0045] It is preferred that the tubular fluororesin inner layer 1 is cooled by a cooling zone 20 provided soon after extrusion molding before it is introduced to the vacuum plasma apparatus 5 as shown in Fig. 11. This is because the tubular fluororesin inner layer just extruded is still hot and soft so that it has poor shape retentivity. It is also preferred that the thermoplastic resin outer layer 2 is cooled by a cooling zone (not shown) provided soon after extrusion molding due to the same reason. In Fig. 11, the same components as shown in Fig. 4 are denoted by the same reference numerals.

[0046] Fig. 4 illustrates the method of producing the fuel hose wherein a mandrel is not used, but the present invention is not particularly limited thereto. The fuel hose may be produced by supplying a mandrel 17 from a mandrel supplier 16 to an inner layer extruder 3 so that a tubular fluororesin inner layer 1 may be formed onto the mandrel 17. In Fig. 12, the construction is the same as in Fig. 4 except that the mandrel supplier 16 and the mandrel 17 are used, and the same components as shown in Fig. 4 are denoted by the same reference numerals.

[0047] In the above description of the procedure for producing a fuel hose, the five production stages of tubular inner layer molding, vacuum plasma treatment, water treatment (or silane coupling agent aqueous solution treatment), drying process and formation of a thermoplastic resin outer layer on the peripheral surface of the inner layer are continuously carried out, but the present invention is not particularly limited thereto. A typical alternative procedure comprises forming a tubular fluororesin inner layer 1 by extruding the material (such as a fluororesin) from the inner layer extruder 3, taking up thereof on a winder (not shown), paying out the tubular inner layer 1 from the winder to the vacuum plasma apparatus 5, the water treatment (or the silane coupling agent aqueous solution treatment), the drying process and molding a thermoplastic resin outer layer on the peripheral surface of the tubular fluororesin inner layer 1. There is the advantage by using such a partial batch process that the materials for the tubular fluororesin inner layer 1 and/or for the thermoplastic resin outer layer 2 can be easily changed for each production lot.

[0048] The fuel hoses as shown in Fig. 2 and 3 may be produced by a braiding process or an extrusion process with a braider or an extruder, for example, provided after the outer layer extruder 14 in Fig. 4.

[0049] The tubular fluororesin inner layer 1 of thus obtained fuel hose according to the present invention has generally an inner diameter of about 4 to 50mm and a thickness of about 0.05 to 1mm and the thermoplastic resin outer layer 2 has a thickness of 0.2 to 4mm, preferably 0.5 to 3mm.

[0050] In the fuel hose according to the present invention, functional groups having oxygen atoms such as OH groups are distributed on the peripheral surface of the tubular fluororesin inner layer. Since the functional groups having oxygen atoms are involved in adhesion, the adhesion strength between the tubular fluororesin inner layer and the thermoplastic resin outer layer can be improved.

[0051] The fuel hose according to the present invention is provided with properties that a strength ratio of bond energy $[I(286-5eV)/I(292.2eV)]$ of surface carbon atoms (C1s) by analyzing the surface layer of the peripheral surface of the tubular fluororesin inner layer with an X-ray photo-electron spectroscopy (ESCA) is not less than 1.3 in the case that bond energy on a peak top of fluorine (F1s) is a standard value (689.63eV) and metal ions are not distributed in the surface layer of the peripheral surface of the tubular fluororesin inner layer. Where the strength ratio of the bond energy is less than 1.3, the surface concentration of fluorine atoms not involved in adhesion is high on the peripheral surface of the tubular fluororesin inner layer so that adhesive strength between the tubular fluorine resin inner layer and the thermoplastic resin outer layer is insufficient. Further, where metal ions (such as Na⁺, Ca²⁺ and Zn²⁺) are

distributed on the surface layer of the tubular fluororesin inner layer, adhesive strength between the tubular fluorine resin inner layer and the thermoplastic resin outer layer is insufficient because the bond strength due to such as hydrogen bonds is prohibited by the metal ions. As such an example, it is known that nylon resin may crack due to an antifreezing agent (such as calcium chloride).

[0052] The analysis by the X-ray photo-electron spectroscopy (ESCA) is preferably using a photoelectron spectrometer (5600Ci available from ULVAC-PHI, INC.) under the following measurement conditions.

Exciting X-rays: A1, $K\alpha_{1,2}$ rays (1486,6 eV)

X-ray output: 10kV, 20mA

Temperature: 20°C


Degree of vacuum: 3×10^{-8} Torr

[0053] Examples will hereinafter be described along with Comparative Examples.

[0054] Prior to Examples and Comparative Examples, the following silane coupling agents were prepared.


Silane coupling agent A

[0055] N- β (aminoethyl) γ -aminopropylmethyldimethoxysilane




Silane coupling agent B

[0056] N- β (aminoethyl) γ -aminopropyltriethoxysilane






Silane coupling agent C

[0057] γ -aminopropyltriethoxysilane



Silane coupling agent D

[0058] γ -aminopropyltriethoxysilane

**Silane coupling agent E**[0059] β -(3,4-epoxycyclohexyl)ethyltrimethoxysilane**Silane coupling agent F**[0060] γ -glycidoxy propyltrimethoxy silane**EXAMPLE 1**

[0061] An ethylene-tetrafluoroethylene copolymer (ETFE) as a material for forming a tubular fluororesin inner layer and nylon 12 (PA12, content of a plasticizer: 5%) as a material for forming a thermoplastic resin outer layer were prepared, as shown in the following Table 1. As a treatment agent, pure water (pH=7) was also prepared. A fuel hose was produced in accordance with a manner shown in Fig. 4 by using these materials. In the thus obtained fuel hose, the tubular fluororesin inner layer had an inner diameter of 6.0mm and a thickness of 0.25mm and the thermoplastic resin outer layer had a thickness of 0.75mm. The plasma treatment conditions were a frequency of 13.56MHz and an output of 250W. In addition, a reaction chamber 6 was evacuated by a vacuum pump 7 to 10^{-3} Torr, and then supplied with a gas containing Ar from a gas supplying apparatus 8 so that the reaction chamber 6 was under a reduced pressure of 0.07 Torr.

EXAMPLE 2

[0062] A fuel hose was produced in the same manner as EXAMPLE 1 except that a 0.1% by weight acetic aqueous acid solution (pH=4 \pm 0.2) was used, as shown in the following Table 1, instead of the pure water (pH=7) of EXAMPLE 1.

EXAMPLE 3

[0063] A fuel hose was produced in the same manner as EXAMPLE 1 except that an aqueous solution of 1% by weight silane coupling agent (A) in pure water (pH=7) was used, as shown in the following Table 2, instead of the pure water (pH=7) of EXAMPLE 1. In addition, the application amount (excluding aqueous solution) of the silane coupling agent was 3×10^{-7} g/cm² based on a plasma-treated peripheral surface of the tubular fluororesin inner layer.

EXAMPLE 4

[0064] A fuel hose was produced in the same manner as EXAMPLE 3 except that the silane coupling agent (B) was used, as shown in the following Table 1, instead of the silane coupling agent (A) of EXAMPLE 3.

EXAMPLE 5

[0065] A fuel hose was produced in the same manner as EXAMPLE 3 except that the silane coupling agent (C) was used, as shown in the following Table 1, instead of the silane coupling agent (A) of EXAMPLE 3.

EXAMPLE 6

[0066] A fuel hose was produced in the same manner as EXAMPLE 3 except that the silane coupling agent (D) was used instead of the silane coupling agent (A) of EXAMPLE 3 and also nylon 11 (PA11) was used as a material for forming a thermoplastic resin outer layer instead of nylon 12 (PA12) of EXAMPLE 3, respectively, as shown in the following Table 1.

EXAMPLE 7

[0067] A fuel hose was produced in the same manner as EXAMPLE 3 except that an aqueous solution of 1% by weight silane coupling agent (E) in an acetic aqueous acid solution ($\text{pH}=4\pm0.2$) was used, as shown in the following Table 2, instead of the acetic aqueous acid solution of 1% by weight silane coupling agent (A) of EXAMPLE 3, as shown in the following Table 2.

EXAMPLE 8

[0068] A fuel hose was produced in the same manner as EXAMPLE 6 except that an aqueous solution of 1% by weight silane coupling agent (F) in an acetic aqueous acid solution ($\text{pH}=4\pm0.2$) was used, as shown in the following Table 2, instead of the aqueous solution of 1% by weight silane coupling agent (D) of EXAMPLE 6, as shown in the following Table 2.

EXAMPLE 9

[0069] A fuel hose was produced in the same manner as EXAMPLE 4 except that a tubular fluororesin inner layer had a two-layer structure of a conductive ETFE inner layer (an inner diameter of 6.0mm and a thickness of 0.10mm) and an ETFE outer layer (a thickness of 0.15mm), as shown in the following Table 2. The above conductive ETFE layer was formed by using a material wherein a conductive carbon black (Ketjen black EC available from Ketjen Black International Company) was mixed at 15% by weight to ETFE.

EXAMPLE 10

[0070] A fuel hose was produced in the same manner as EXAMPLE 4 except that conductive PA12 was used for forming a thermoplastic resin outer layer instead of nylon 12 (PA12) of EXAMPLE 4, the conductive PA12 having a conductive carbon black (Ketjen black EC available from Ketjen Black International Company) mixed at 13% by weight to PA12, as shown in the following Table 2.

EXAMPLE 11

[0071] A fuel hose was produced in the same manner as EXAMPLE 1 except that a tubular fluororesin inner layer was formed by using polyvinylidene fluoride (PVDF) and the tubular fluororesin inner layer was treated with an aqueous solution of 0.2% by weight silane coupling agent (B) in pure water ($\text{pH}=7$) and nylon 11 (PA11) was used for forming a thermoplastic resin outer layer, as shown in the following Table 2.

EXAMPLE 12

[0072] A fuel hose was produced in the same manner as EXAMPLE 1 except that a tubular fluororesin inner layer was formed by using a tetrafluoroethylene-hexafluoropropylene-vinylidene fluoride terpolymer (THV) and the tubular fluororesin inner layer was treated with an aqueous solution of 0.5% by weight silane coupling agent (D) in pure water

(pH=7) and nylon 6 (PA6) was used for forming a thermoplastic resin outer layer, as shown in the following Table 2.

EXAMPLE 13

[0073] A fuel hose was produced in the same manner as EXAMPLE 9 except that a conductive carbon black (Denka black available from Denki Kagaku Kogyo K.K.) was used instead of the carbon black (Ketjen black EC available from Ketjen Black International company).

COMPARATIVE EXAMPLE 1

[0074] A fuel hose was produced in the same manner as EXAMPLE 1 except that water treatment was not conducted, as shown in the following Table 3.

COMPARATIVE EXAMPLE 2

[0075] A fuel hose was produced in the same manner as EXAMPLE 11 except that treatment with silane coupling agent aqueous solution was not conducted, as shown in The following Table 3.

COMPARATIVE EXAMPLE 3

[0076] A fuel hose was produced in the same manner as EXAMPLE 1 except that plasma treatment was not conducted, as shown in the following Table 3.

COMPARATIVE EXAMPLE 4

[0077] A fuel hose was produced in the same manner as EXAMPLE 1 except that corona treatment was conducted instead of plasma treatment, as shown in the following Table 3. In addition, the corona treatment was conducted in the air by using an apparatus shown in Fig. 13 with a frequency of 20kHz and an output of 0.4kw. In Fig. 13, there are shown a high-frequency power source 31 and electrodes 39.

COMPARATIVE EXAMPLE 5

[0078] A fuel hose was produced in the same manner as EXAMPLE 1 except that a solution of 20% by volume epoxy resin adhesive in ethanol (BX60 available from Toagosei Co., Ltd.) was used as a treatment agent, as shown in the following Table 3.

COMPARATIVE EXAMPLE 6

[0079] A fuel hose was produced in the same manner as EXAMPLE 1 except that a 1% by weight aqueous solution (pH=11) of sodium hydroxide was used as a treatment agent, as shown in the following Table 3.

COMPARATIVE EXAMPLE 7

[0080] A fuel hose was produced in the same manner as EXAMPLE 7 except that a solution of 3% by weight silane coupling agent (E) in ethanol was used as a treatment agent instead of the acetic aqueous acid solution of 1% by weight silane coupling agent (E) of EXAMPLE 7, as shown in the following Table 4.

COMPARATIVE EXAMPLE 8

[0081] A fuel hose was produced in the same manner as EXAMPLE 8 except that a solution of 3% by weight silane coupling agent (F) in ethanol was used as a treatment agent instead of the acetic aqueous acid solution of 3% by weight silane coupling agent (F) of EXAMPLE 8, as shown in the following Table 4.

[0082] For each of the above fuel hoses of the EXAMPLES and the COMPARATIVE EXAMPLES, each adhesive strength, at an initial stage, after immersion in gasoline and after heat aging was determined according to the following standards. These results are also shown in the following Tables 1 to 4. For each of the fuel hoses of EXAMPLES 1 and 2 and COMPARATIVE EXAMPLES 1 and 6, the treated surface of the tubular fluororesin inner layer was analyzed by an X-ray photo-electron spectroscopy (ESCA). The results are shown in the following Tables 1 to 4 and Figs. 15 and 16.

Initial adhesive strength

[0083] The initial adhesive strength was determined in accordance with JIS K 6301. Thus, as illustrated in Fig. 14, each fuel hose was sliced into a 10mm-long ring which was then cut in the longitudinal direction to prepare a test sample. The tubular fluororesin inner layer 1 and the thermoplastic resin outer layer 2 of this sample were partially peeled off from the section and the peeled ends were secured stationarily with the jig of a tensile tester and a tensile test was performed at a peeling speed of 25mm/min. The load found from this tensile test was regarded as the initial adhesive strength between the two layers.

Adhesive strength after immersion in gasoline

[0084] The test piece prepared in the same manner as the above determination of the initial adhesive strength was immersed in gasoline (Fuel C) at 40°C for 168 hours and the adhesive strength between the tubular fluororesin inner layer 1 and the thermoplastic resin outer layer 2 was determined in the same manner as described above.

Adhesive strength after heat aging

[0085] The test piece prepared in the same manner as the above determination of the initial adhesive strength was heat-treated at 125°C for 240 hours and the adhesive strength between the tubular fluororesin inner layer 1 and the thermoplastic resin outer layer 2 was determined in the same manner as described above.

ESCA analysis

[0086] The treated surface (peripheral surface) of the tubular fluororesin inner layer of the fuel hose was analyzed by using an X-ray photo-electron spectroscopy (5600Ci available from ULVAC-PHI, INC.) under the following conditions. In addition, the tubular fluororesin inner layer was preserved under reduced pressure immediately after the pre-determined surface treatment and was immediately subject to this analysis in order to prevent effects from the atmosphere (the air or moisture) from the surface treatment process (plasma treatment or plasma treatment + water treatment) on the tubular fluororesin inner layer to the coating process on the thermoplastic resin outer layer.

Exciting X-rays: A1, $K\alpha_{1,2}$ rays (1486.6eV9)

X-ray output: 10kV, 20mA

Temperature: 20°C

Degree of vacuum: 3×10^{-8} Torr

TABLE 1

	EXAMPLES					
	1	2	3	4	5	6
Tubular fluororesin inner layer	ETFE	ETFE	ETFE	ETFE	ETFE	ETFE
surface treatment	plasma treatment	plasma treatment	plasma treatment	plasma treatment	plasma treatment	plasma treatment
Treatment agent						
Silane coupling agent	pure water (pR=7)	acetic acid solution	A	B	C	D
Solvent			pure water	pure water	pure water	pure water
Concentration (% by weight)			1	1	1	1
Thermoplastic resin outer layer	PA12	PA12	PA12	PA12	PA12	PA11

TABLE 1 (continued)

	EXAMPLES					
	1	2	3	4	5	6
Adhesive strength (N/mm)						
At an initial stage	3.5	4.0	4.0	3.5	3.5	3.6
After immersion in gasoline	3.0	3.2	3.1	3.1	3.3	3.3
After heat aging	3.0	2.9	3.3	3.3	3.2	3.3
ESCA analysis I (286.5eV)/I (292.2eV)	2.0	2.3	-	-	-	-

TABLE 2

	EXAMPLES						
	7	8	9	10	11	12	13
Tubular fluoro-resin inner layer	ETFE	ETFE	c-ETFE/ETFE	ETFE	PVDF	THV	c-ETFE/ETFE
Surface treatment	plasma treatment	plasma treatment	plasma treatment	plasma treatment	plasma treatment	plasma treatment	plasma treatment
Treatment agent							
Silane coupling agent	E	F	B	B	B	D	B
Solvent	acetic acid	acetic acid	pure water	pure water	pure water	pure water	pure water
Concentration (% by weight)	1	1	1	1	0.2	5	1
Thermoplastic resin outer layer	PA12	PA11	PA12	c-PA12	PA11	PA6	PA12
Adhesive strength (N/mm)							
At an initial stage	3.8	3.8	4.0	3.7	3.8	material rupture *	4.0
After immersion in gasoline	3.3	3.2	3.1	3.1	3.0	material rupture *	3.1
After heat aging	3.3	3.4	3.3	3.1	3.3	material rupture *	3.3
ESCA analysis I (286.5eV)/I (292.2eV)	-	-	-	-	-	-	-

*The tubular fluoro-resin inner layer ruptured since adhesion was strong.

TABLE 3

	COMPARATIVE EXAMPLES					
	1	2	3	4	5	6
Tubular fluororesin inner layer	ETFE	PVDF	ETFE	ETFE	ETFE	ETFE
Surface treatment	plasma treatment	plasma treatment	-	corona treatment	plasma treatment	plasma treatment
Treatment agent	-	-	pure water (pH=7)	pure water (pH=7)	epoxy resin adhesive	NaOH aqueous solution (pH=11)
Thermoplastic resin outer layer	PA12	PA11	PA12	PA12	PA12	PA12
Adhesive strength (N/mm)						
At an initial stage	3.5	3.6	0.1	1.3	2.0	1.7
After immersion in gasoline	2.5	2.4	0	0.7	1.7	0.4
After heat aging	2.6	2.6	0	1.1	1.8	1.3
ESCA analysis I (286.5eV)/I (292.2eV)	0.9	-	-	-	-	2.2 (Na detected)

TABLE 4

	COMPARATIVE EXAMPLES	
	7	8
Tubular fluororesin inner layer	ETFE	ETFE
Surface treatment	plasma treatment	plasma treatment
Treatment agent		
Silane coupling agent	E	F
Solvent	ethanol	ethanol
Concentration (% by weight)	3	3
Thermoplastic resin outer layer	PA12	PA11
Adhesive strength (N/mm)		
At an initial stage	3.7	3.7
After immersion in gasoline	3.0	2.9
After heat aging	3.2	3.2
ESCA analysis I(286.5eV)/I(292.2eV)	-	-

[0087] As can be understood from the results of the above Tables 1 to 4, each fuel hose of the EXAMPLES had

sufficient adhesive reliability since initial adhesive strength was excellent and also deterioration in adhesive strength after immersion in gasoline and after heat aging was restrained. As can be understood from the results of ESCA analysis, each fuel hose of EXAMPLES 1 and 2 had a strength ratio of bond energy [$I(286.5\text{eV})/I(292.2\text{eV})$] of not less than 1.3. Fig. 15 is a chart for data when bond energy of fluorine (F1s) at a peak top is a standard value (689.63eV). Fig. 16 (a) shows a chart for data of a sample without plasma treatment, Fig. 16 (b) shows a chart for data of a sample conducted with plasma treatment (COMPARATIVE EXAMPLE 1) and Fig. 16 (c) shows a chart for data of a sample conducted with plasma treatment and water treatment (EXAMPLE 1). Comparing Fig. 16 (a) with Fig. 16 (b), the strength peak at 292.2eV due to CF_2 groups in bond energy strength of surface carbon atoms (C1s) decreased because of elimination of fluorine atoms by plasma treatment so that the surface concentration of fluorine atoms decreased. Comparing Fig. 16 (b) with Fig. 16 (c); the surface concentration of fluorine atoms further decreased by conducting water treatment after plasma treatment and a peak (286.5eV) due to CH_2 groups shifted to a low energy side. It is thought that the functional groups having fluorine atoms not involved in adhesion go inside the tubular fluororesin inner layer by conducting water treatment on the plasma-treated peripheral surface so that the surface concentration of fluorine atoms is decreased on the peripheral surface of the tubular fluororesin inner layer and adhesive functional groups (functional groups having oxygen atoms) such as an OH group is increased.

[0088] On the other hand, each fuel hose of COMPARATIVE EXAMPLES 1 and 2 was treated with neither water nor silane coupling agent aqueous solution after plasma treatment and therefore was inferior in each adhesive strength after immersion in gasoline and after heat aging. From the results of ESCA analysis, the fuel hose of COMPARATIVE EXAMPLE 1 had a strength ratio of bond energy [$I(286.5\text{eV})/I(292.2\text{eV})$] of not more than 1.3. The fuel hose of COMPARATIVE EXAMPLE 3 was remarkably inferior in initial adhesive strength since plasma treatment was not conducted, resulting in each adhesive strength of 0 (N/mm) after immersion in gasoline and heat aging. The fuel hose of COMPARATIVE EXAMPLE 4 was inferior in initial adhesive strength since corona treatment was conducted without plasma treatment, resulting in an inferior adhesive strength after immersion in gasoline and after heat aging. The fuel hose of COMPARATIVE EXAMPLE 5 was remarkably inferior in an adhesive strength after immersion in gasoline and after heat aging since it was treated with epoxy resin adhesive, resulting in inferior adhesive reliability. In the fuel hose of COMPARATIVE EXAMPLE 6, functional groups having oxygen atoms increased as well as EXAMPLE 1 where water treatment was conducted, but initial adhesive strength was inferior and adhesive strengths after immersion in gasoline and after heat aging were inferior since it was conducted with a sodium hydroxide aqueous solution. It is thought that the bond strength due to such as hydrogen bonds is prohibited by sodium ions and the strength of the thermoplastic resin outer layer was decreased also by sodium ions. As such an example, it is known that nylon resin may crack due to an antifreezing agent (such as calcium chloride). In addition, the adhesive strengths at an initial stage and also after immersion in gasoline and heat aging of the fuel hose of COMPARATIVE EXAMPLE 7 where an ethanol solution of the silane coupling agent was used were slightly inferior as compared with the fuel hose of EXAMPLE 7 where an acetic aqueous acid solution of the silane coupling agent was used. Similarly, the adhesive strengths at an initial stage and also after immersion in gasoline and heat aging of the fuel hose of COMPARATIVE EXAMPLE 8 where an ethanol solution of the silane coupling agent was used were slightly inferior as compared with the fuel hose of EXAMPLE 8 where an acetic aqueous acid solution of the silane coupling agent was used. Further, for preparation of each fuel hose of COMPARATIVE EXAMPLES 7 and 8, the organic solvent such as ethanol was used for diluting the silane coupling agent. Thus, concerns are expected about adverse effects on a working environment and a global environment due to transpiration of an organic solvent in the atmosphere. Further, special equipment for combustible materials is required, which is inferior in workability.

EFFECT OF THE INVENTION

[0089] As described above, the fuel hose of the present invention can be obtained by plasma-treating the surface of the tubular fluororesin inner layer, conducting at least one of water treatment and silane coupling agent aqueous solution treatment on the plasma-treated peripheral surface and forming the thermoplastic resin outer layer on the treated peripheral surface. Thus, the functional groups having fluorine atoms not involved in adhesion go inside the tubular fluororesin inner layer by conducting the at least one treatment on the plasma-treated peripheral surface so that the surface concentration of fluorine atoms is decreased on the peripheral surface of the tubular fluororesin inner layer and adhesive functional groups (functional groups having oxygen atoms) such as an OH group are widely distributed therein. As a result, the adhesive strength between the tubular fluororesin inner layer and the thermoplastic resin outer layer is improved so that deterioration in adhesive strength after heat aging and immersion into fuel can be restrained under severe conditions such as an inside of an engine compartment, for obtaining a fuel hose superior in adhesive reliability. Especially, where the silane coupling agent aqueous solution treatment is conducted on the peripheral surface of the plasma-treated peripheral surface, a silane coupling agent layer can be formed on the surface of the tubular fluororesin inner layer so that the adhesive strength between the tubular fluororesin inner layer and the silane coupling agent layer, and between the silane coupling agent layer and the thermoplastic resin outer layer, can

be further enhanced.

[0090] Where the water treatment is conducted by using an aqueous acid solution, sufficient adhesive strength after heat aging and immersion into fuel can be obtained so that a fuel hose further superior in adhesive reliability can be produced. Where a hydrogen exponent (pH) of the aqueous acid solution is 2 to 6, 8 fuel hose even further superior in adhesive reliability can be produced.

[0091] Where the silane coupling agent is an amino silane coupling agent represented by the above-mentioned general formula (1), stability of the silane coupling agent aqueous solution is improved. Where the concentration of the silane coupling agent is not more than 10% by weight of a total amount of the aqueous solution, it becomes easy to treat the plasma-treated peripheral surface with silane coupling agent.


[0092] Where a hydrogen exponent (pH) of the acid silane coupling agent aqueous solution is 2 to 6, sufficient adhesive strength after heat aging and immersion into fuel can be obtained, resulting in superior adhesive reliability. Where the silane coupling agent is an epoxy silane coupling agent represented by the above-mentioned general formula (2), stability of the silane coupling agent aqueous solution is improved. Where the concentration of the silane coupling agent is not more than 10% by weight of a total amount of the aqueous acid solution, it becomes easy to treat the plasma-treated peripheral surface with silane coupling agent acid solution.

[0093] In addition, since silane coupling agents are flammable, a special installation for combustible materials is required for use thereof. For this reason, a silane coupling agent is generally diluted with an organic solvent such as alcohol for use, which, however, may cause adverse effects on a working environment and a global environment due to transpiration of an organic solvent in the atmosphere. According to the present invention where the silane coupling agent aqueous solution diluted with water or silane coupling agents is used without organic solvents such as alcohols, a special installation for combustible materials is not necessary, thereby obtaining superior safety because of no fear about fire, improved workability and prevention of air pollution.

[0094] The features disclosed in the foregoing description, in the following claims and/or in the accompanying drawings may, both separately and in any combination thereof, be material for realising the invention in diverse forms thereof.

Claims

1. A method of producing a fuel hose comprising plasma-treating a surface of a tubular fluororesin inner layer, treating a surface layer of the plasma-treated peripheral surface with at least one of water and a silane coupling agent aqueous solution and forming a thermoplastic resin outer layer on the treated peripheral surface.
2. The method according to claim 1, wherein the water treatment is conducted by using an aqueous acid solution.
3. The method according to claim 2, wherein the aqueous acid solution has a hydrogen exponent (pH) of 2 to 6.
4. The method according to claim 1, wherein the silane coupling agent is an amino silane coupling agent represented by the following general formula (1):




wherein Y is $NH_2(CH_2)_n-$, $NH_2(CH_2)_nNH(CH_2)_m-$ or $NH_2CONH(CH_2)_n-$, wherein n and m are 0 to 5, respectively, X^1 , X^2 and X^3 , which are the same or different, are $-CH_3$, $-OCH_3$, $-OC_2H_5$ or $-OC_2H_4OCH_3$, respectively, wherein at least two of X^1 , X^2 and X^3 are $-OCH_3$, $-OC_2H_5$ or $-OC_2H_4OCH_3$.

5. The method according to claim 1 or 4, wherein the concentration of the silane coupling agent is not more than 10% by weight of a total amount of the aqueous solution.
6. The method according to claim 1, wherein the silane coupling agent aqueous solution is an acid silane coupling agent aqueous solution.


7. The method according to claim 6, wherein the acid silane coupling agent aqueous solution has a hydrogen exponent

(pH) of 2 to 6.


8. The method according to claim 6 or 7, wherein the silane coupling agent is an epoxy silane coupling agent represented by the following general formula (2):



wherein Z is



or



wherein n is 0 to 5,

X¹, X² and X³, which are the same or different, are -CH₃, -OCH₃, -OC₂H₅ or -OC₂H₄OCH₃, respectively, wherein at least two of X¹, X² and X³ are -OCH₃, -OC₂H₅ or -OC₂H₄OCH₃.

9. The method according to any of claims 6 to 8, wherein the concentration of the silane coupling agent is not more than 10% by weight of a total amount of the aqueous acid solution.
10. The method according to any of claims 1 to 9, wherein the tubular fluororesin inner layer includes an ethylene-tetrafluoroethylene copolymer.
11. The method according to any of claims 1 to 10, wherein the tubular fluororesin inner layer comprises at least two layers of which an innermost layer includes a conductive fluororesin and an outermost layer includes a non-conductive fluororesin.
12. The fuel hose produced by the method according to any of claims 1 to 11, wherein a functional group containing an oxygen atom is distributed in a surface layer of the peripheral surface of the tubular fluororesin inner layer.
13. The fuel hose according to claim 12, wherein a strength ratio of bond energy [I(286.5eV)/I(292.2eV)] of surface carbon atoms (C1s) by analyzing the surface layer of the peripheral surface of the tubular fluororesin inner layer by means of an X-ray photo-electron spectroscopy (ESCA) is not less than 1.3 in the case that bond energy on a peak top of fluorine (F1s) is a standard value (689.63eV) and metal ions are not distributed in the surface layer of the peripheral surface of the tubular fluororesin inner layer.
14. The fuel hose produced by the method according to claim 1, comprising a tubular fluororesin inner layer and a thermoplastic resin outer layer formed on a peripheral surface of the tubular fluororesin inner layer, wherein the thermoplastic resin outer layer includes polyamide resin.
15. The fuel hose produced by the method according to claim 14, wherein the tubular fluororesin inner layer comprises at least two layers, an innermost layer of said at least two layers includes conductive fluororesin and an outermost

layer of said at least two layers includes non-conductive fluororesin.

16. The fuel hose according to claim 14 or 15, wherein a rubber layer or a thermoplastic elastomer layer is on a peripheral surface of the thermoplastic resin outer layer.

17. A fuel-hose comprising: a plasma-treated fluororesin inner layer, a surface layer of the inner layer being treated with at least one of water and a silane coupling agent aqueous solution; and a thermoplastic resin outer layer.




Fig. 1




Fig. 2




Fig. 3




Fig. 4




Fig. 5




Fig. 6




Fig. 7




Fig. 8




Fig. 9




Fig. 10




Fig. 11




Fig. 12




Fig. 13




Fig. 14





Fig. 15



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11)

EP 0 979 968 A3

(12)

EUROPEAN PATENT APPLICATION

(88) Date of publication A3:
18.04.2001 Bulletin 2001/16

(51) Int Cl.7: **F16L 11/04**, B29C 59/14,
C08J 7/06, B32B 1/08
// B29K27:12

(43) Date of publication A2:
16.02.2000 Bulletin 2000/07

(21) Application number: **99306286.8**

(22) Date of filing: **09.08.1999**

(84) Designated Contracting States:
**AT BE CH CY DE DK ES FI FR GB GR IE IT LI LU
MC NL PT SE**
Designated Extension States:
AL LT LV MK RO SI

- Ito, Hiroaki
Kasugai-shi, Aichi 487-0035 (JP)
- Nishiyama, Takahiro
Kasugai-shi, Aichi 486-0903 (JP)
- Murakami, Koyo
Nagoya-shi, Aichi 464-0035 (JP)
- Hayakawa, Tomonori
Tokai-shi, Aichi 476-0002 (JP)

(30) Priority: **10.08.1998 JP 22508798**
10.08.1998 JP 22508898

(71) Applicant: **TOKAI RUBBER INDUSTRIES, LTD.**
Komaki-shi, Aichi-ken, 485-8550 (JP)

(74) Representative: **Frankland, Nigel Howard**
FORRESTER & BOEHMERT
Franz-Joseph-Strasse 38
80801 München (DE)

(72) Inventors:
• **Katayama, Kazutaka**
Komaki-shi, Aichi 485-0029 (JP)

(54) **Method of producing fuel hose and fuel hose obtained thereby**

(57) A method of producing a fuel hose having superior adhesive reliability with superior initial adhesive strength between a tubular fluororesin inner layer (1) and a thermoplastic resin outer layer (2) and with restrained deterioration in adhesive strength after heat aging and immersion into fuel under severe conditions such as an inside of an engine compartment. The method includes plasma treatment on a peripheral surface of the tubular fluororesin inner layer, at least one treatment of water treatment and silane coupling agent treatment on the plasma-treated surface and formation of the thermoplastic resin outer layer on the treated peripheral surface. Thus, the functional groups having fluorine atoms not involved in adhesion go inside the tubular fluororesin inner layer by conducting the at least one treatment of water treatment and silane coupling agent aqueous solution treatment so that the surface concentration of fluorine atoms sufficiently decreases on the peripheral surface of the tubular fluororesin inner layer and adhesive functional groups (functional groups having oxygen atoms) such as an OH group are widely distributed therein. As a result, adhesive strength between the tubular fluororesin inner layer and the thermoplastic resin outer layer is improved so that deterioration in adhesive strength after heat aging and immersion into fuel can be restrained under severe conditions such as an inside of

an engine compartment, for obtaining a fuel hose superior in adhesive reliability.




Fig. 1

EP 0 979 968 A3



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 30 6286

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
X	EP 0 479 592 A (BRIDGESTONE CORP ; OKAZAKI SATIKO (JP); KOGOMA MASUHIRO (JP)) 8 April 1992 (1992-04-08) * page 1, line 4 - page 1, line 20 * * page 1, line 59 - page 2, line 10 * * page 4, line 17 - page 4, line 18 * * examples *	1, 10, 12, 17	F16L11/04 B29C59/14 C08J7/06 B32B1/08 //B29K27:12
Y	---	2-9, 11	
Y	EP 0 829 507 A (DAICEL CHEM) 18 March 1998 (1998-03-18) * page 9, line 23 - page 10, line 39 *	2-9, 11	
X	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 06, 30 April 1998 (1998-04-30) & JP 10 030764 A (TOKAI RUBBER IND LTD), 3 February 1998 (1998-02-03) * abstract *	1, 12, 17	
Y	EP 0 551 094 A (PILOT IND INC) 14 July 1993 (1993-07-14) * page 3, line 24 - page 3, line 37 * * page 4, line 4 - page 5, line 12 *	1-17	TECHNICAL FIELDS SEARCHED (Int.Cl.7)
Y	WO 95 23036 A (PILOT IND INC) 31 August 1995 (1995-08-31) * page 4, line 1 - page 4, line 31 *	1-17	F16L B29C C08J B32B
A	EP 0 676 276 A (TOKAI RUBBER IND LTD) 11 October 1995 (1995-10-11) * page 4, line 31 - page 5, line 28 *	1-17	
A	US 5 500 257 A (KUENZEL KENNETH J ET AL) 19 March 1996 (1996-03-19) * page 4, line 51 - page 5, line 50 *	1-17	

	-/--		
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 15 February 2001	Examiner Schweissguth, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document</p> <p>T: theory or principle underlying the invention E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</p>			

EPO FORM 1503 (03.02) (P04001)



European Patent
Office

EUROPEAN SEARCH REPORT

Application Number
EP 99 30 6286

DOCUMENTS CONSIDERED TO BE RELEVANT			
Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int.Cl.7)
A	US 4 735 996 A (NAGAI ITSUO ET AL) 5 April 1988 (1988-04-05) * the whole document *	1-17	
A	PATENT ABSTRACTS OF JAPAN vol. 1998, no. 06, 30 April 1998 (1998-04-30) & JP 10 030765 A (TOKAI RUBBER IND LTD), 3 February 1998 (1998-02-03) * abstract *	1-17	
			TECHNICAL FIELDS SEARCHED (Int.Cl.7)
The present search report has been drawn up for all claims			
Place of search MUNICH		Date of completion of the search 15 February 2001	Examiner Schweissguth, M
<p>CATEGORY OF CITED DOCUMENTS</p> <p>X : particularly relevant if taken alone Y : particularly relevant if combined with another document of the same category A : technological background O : non-written disclosure P : intermediate document</p> <p>T : theory or principle underlying the invention E : earlier patent document, but published on, or after the filing date D : document cited in the application L : document cited for other reasons & : member of the same patent family, corresponding document</p>			

EPO FORM 1503 03/02 (P04001)

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 30 6286

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report. The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-02-2001

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
EP 0479592 A	08-04-1992	JP 3057742 B	04-07-2000
		JP 4145139 A	19-05-1992
		DE 69110823 D	03-08-1995
		DE 69110823 T	21-12-1995
		JP 5125202 A	21-05-1993
		US 5425832 A	20-06-1995
		JP 3094644 B	03-10-2000
		JP 5309787 A	22-11-1993
EP 0829507 A	18-03-1998	JP 10076593 A	24-03-1998
		CN 1176173 A	18-03-1998
		SG 64440 A	27-04-1999
		US 5942320 A	24-08-1999
JP 10030764 A	03-02-1998	NONE	
EP 0551094 A	14-07-1993	AT 165273 T	15-05-1998
		AU 665598 B	11-01-1996
		AU 3101493 A	08-07-1993
		BR 9300057 A	13-07-1993
		CA 2086032 A,C	07-07-1993
		DE 69318043 D	28-05-1998
		DE 69318043 T	13-08-1998
		ES 2114959 T	16-06-1998
		JP 5245989 A	24-09-1993
		JP 8005167 B	24-01-1996
		KR 190411 B	01-06-1999
		MX 9300020 A	28-02-1994
		US 5759329 A	02-06-1998
		US 5958532 A	28-09-1999
		US 5554425 A	10-09-1996
		US 5500257 A	19-03-1996
		US 5916404 A	29-06-1999
WO 9523036 A	31-08-1995	AU 681898 B	11-09-1997
		AU 7316894 A	11-09-1995
		BR 9408554 A	05-08-1997
		DE 814917 T	25-02-1999
		EP 0814917 A	07-01-1998
		ES 2116948 T	01-08-1998
		JP 9509377 T	22-09-1997
		KR 232558 B	01-12-1999
		US 5554425 A	10-09-1996
		US 5500257 A	19-03-1996
		US 5916404 A	29-06-1999

EPO FORM P0469 For more details about this annex : see Official Journal of the European Patent Office, No. 12/82

**ANNEX TO THE EUROPEAN SEARCH REPORT
ON EUROPEAN PATENT APPLICATION NO.**

EP 99 30 6286

This annex lists the patent family members relating to the patent documents cited in the above-mentioned European search report.
The members are as contained in the European Patent Office EDP file on
The European Patent Office is in no way liable for these particulars which are merely given for the purpose of information.

15-02-2001

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 0676276	A	11-10-1995	US 5718957 A	17-02-1998
			CN 1115568 A,B	24-01-1996
			WO 9507176 A	16-03-1995
			US 5919326 A	06-07-1999
			JP 7178875 A	18-07-1995
US 5500257	A	19-03-1996	AU 681898 B	11-09-1997
			AU 7316894 A	11-09-1995
			BR 9408554 A	05-08-1997
			DE 814917 T	25-02-1999
			EP 0814917 A	07-01-1998
			ES 2116948 T	01-08-1998
			JP 9509377 T	22-09-1997
			KR 232558 B	01-12-1999
			WO 9523036 A	31-08-1995
			US 5554425 A	10-09-1996
			US 5916404 A	29-06-1999
			AT 165273 T	15-05-1998
			AU 665598 B	11-01-1996
			AU 3101493 A	08-07-1993
			BR 9300057 A	13-07-1993
			CA 2086032 A,C	07-07-1993
			DE 69318043 D	28-05-1998
			DE 69318043 T	13-08-1998
			EP 0551094 A	14-07-1993
			ES 2114959 T	16-06-1998
			JP 5245989 A	24-09-1993
			JP 8005167 B	24-01-1996
			KR 190411 B	01-06-1999
			MX 9300020 A	28-02-1994
			US 5759329 A	02-06-1998
			US 5958532 A	28-09-1999
US 4735996	A	05-04-1988	JP 1864251 C	08-08-1994
			JP 5068496 B	29-09-1993
			JP 60009734 A	18-01-1985
JP 10030765	A	03-02-1998	NONE	

EPO FORM P0489

For more details about this annex : see Official Journal of the European Patent Office, No. 12/82